3D Laminates

For protective surfacing of flat and 3D retail fixture components





Durability By Design®

KYDEX[®] 3D Laminates

Thermoplastic Alloy Formulated for Durability and Performance

KYDEX® 3D Laminates are formulated for extreme resistance to impact and harsh cleansers. It is fire resistant and self-extinguishing. Engineered to be flat laminated or formed over components, it can be routed with deep recesses for cutting edge retail fixture components.

Protect the long-term performance of retail fixture components with damage-resistant KYDEX[®] 3D Laminates.



MDF board was routed, membrane pressed, and mitre-folded to produce durable, drop-front shelving for Smithsonian Museum Stores.

Impact and Puncture Resistant

KYDEX[®] 3D Laminates provide significantly better impact and puncture resistance than high-pressure laminates (HPLs) and low-pressure laminates (LPLs or melamine) which tend to chip, crack or break in high traffic areas.

Forms to Compound Corners and Contoured Edges

KYDEX® 3D Laminates seamlessly encapsulate the top and side surfaces of routed wood substrates. This allows for production of parts with compound curves, undercut edges, fine details, and sharp or rounded corners-and even brand identifications and wire management holes.

Components made using KYDEX[®] 3D Laminates appear to be machined from solid wood, solid aluminum, granite, or solid surfacing, and can be produced far more economically than with traditional methods.

Minimises the need for Moulding and Edge Banding

With KYDEX[®] 3D Laminates, seamless cladding of 3D components eliminates edge banding, T-moulding, sharp edges, unsafe corners, and delamination problems associated with HPLs and LPLs.

Wide Range of Colours, Textures, and Patterns

KYDEX[®] 3D Laminates are offered in a wide range of solid colours, metallics, granite patterns, and highly realistic wood grains. This enables fixture components to closely simulate components machined from the finest solid materials, both in shape and in finish.

Matching Other Surface Materials

It is now possible to mix and match KYDEX[®] 3D Laminates with popular HPLs, melamine boards—including those of Flakeboard® Formica[®], Roseburg[®], Tafisa[®], Wilsonart[®], and others.

State-of-the-Art Applications

KYDEX[®] 3D Laminates provide the freedom to design state-of-the-art, three-dimensional store fixture components that simulate more expensive, solid materials:

- Kiosks
- Checkout counters
- Cabinetry
- Exhibits and displays
- Door and drawer fascias
- Mouldings
- Pedestals and stands of all types
- Transaction surfaces
- Workstations
- Kickplates and pushplates
- · Logo and trademark panels
- Tabletops
- Shop fittings
- Flat-laminated panels of all types
- And much, much more

Production Methods

Membrane Pressing

Membrane pressing uses vacuum and pressure to apply heated KYDEX 3D Laminate onto a wood or composite substrate. The substrate can be routed to any three-dimensional shape including compound curves, undercut edges, profiles, sharp details and rounded corners:

- Conforming fully to the core
- Ability to create three-dimensional contours and seamless edges with compound curves
- Preservation of sharp edges and surface detail
- Maintenance of uniform wall thickness on high spots, low spots, and sharp corners
- Ability to form around bottom bevels for total encapsulation

Laminating and Mitre Folding

Lamination with KYDEX® sheet results in a protective, attractive surface that does not chip, crack, break, or snap like HPLs, to withstand abuse in high-traffic retail, institutional, and commercial interiors.

- Integral colour (depending on grade) to eliminate black seams
- Available in a range of thicknesses
- A wide choice of substrates, such as wood, metal, gypsum, and rigid foam
- Use of commercially available adhesives and hot- or cold-pressing production methods
- Ability to mitre fold to produce seamless edges



- - welding

Forming, Fabricating, and Machining

The diversity of methods to effectively form, fabricate, machine, and join KYDEX® 3D Laminates—without the cracking, chipping, or snapping associated with many thermoplastic and thermoset sheet products-opens limitless application possibilities.

 Machining with conventional power tools (saw, die cut, shear, rout, drill, sand, file, mill) • Post forming, brake forming, and heat

• Joining with screws, rivets, other common fasteners, or commercially available adhesives

• Appropriate for formed and/or laminated products requiring simple or complex secondary operations

KYDEX[®] sheet is also offered in heavier gauges that are self-supporting and can be utilised without a substrate for fabrication, forming, and machining of brackets, partitions, housings, and other accessories to match fixture components.

KYDEX, LLC can help you find membrane-pressing resources.

Comparison of KYDEX® 3D Laminate and HPL subject to similar impact.

> KYDEX[®] 3D Laminates can cover compound corners without edge banding.

3D Laminates

	Description
KYDEX® HD Integral Colours	High durability, Class I/A fire rated sheet with integral colour in 0.56 mm (0.022") thickness—the thinnest KYDEX® sheet offered—developed specifically for membrane pressing applications. Improves edge definition, post-press trimming, and press cycle times, while surpassing HPLs, and melamine in resistance to surface and edge impact. Available in roll and sheet stock.
KYDEX® XD Integral Colours	Specialised Class 1/A grade of KYDEX [®] sheet in 0.76 mm (0.030") and 1.02 mm (0.040") thickness offers extreme durability. Intended for flat and 3D laminating of building products exposed to high traffic, and offered in 36 standard colours, 4,000 custom colours, and six textures. Excellent for mitre-folding applications.
KYDEX [®] WG Wood Grain Cap	High impact, fire rated sheet in 0.76 mm (0.030") thickness with colour matched substrate and permanently fused to a high performance cap film with highly realistic wood grain patterns. Developed specifically for membrane pressing applications, thin-gauge KYDEX wood grain sheet improves edge definition, post-press trimming, and press cycle times, and stands up to extreme abuse in retail environments while simulating components milled of the finest solid hardwoods. Offered in 13 stock wood grain patterns that match melamine, and HPLs. Available in roll and sheet stock.
KYDEX [®] 152 WG Wood Grain Cap	Super tough KYDEX [®] sheet in 1.02 mm (0.040") thickness offers a higher level of durability. Available in the same patterns as KYDEX [®] WG plus several custom wood grain patterns; each substrate colour is custom matched to complement the wood grain cap. Class I/A rated when tested according to ASTM E-84. NOTE: Depending on sheet size, pattern may be centered on sheet. May not print to edge.
KYDEX [®] 130 Integral Granite	High-performance KYDEX [®] sheet with integral granite pattern to simulate solid surfaces. Available in five colours. Class I/A rated for non-wallcovering applications.
KYDEX® 510 Granite Cap	KYDEX [®] sheet of any colour with a clear, weatherable cap that is reverse-printed with black/white.
KYDEX® 110 Integral Metallic	Super tough metallic-coloured KYDEX [®] sheet that sets new standards for 3D laminating applications in impact resistance, formability, fire retardancy, and aesthetics.

		Thicknesses/Textures								Colours/Patterns								
Flammability Class 1/A (ASTM E-84)	Impact Resistance Gardner Drop Dart (25.40 mm [1.0"] MDF)	0.56 mm (0.022")	0.71 mm (0.028")	0.76 mm (0.030")	1.02 mm (0.040")	P-E Smooth Nap	P-C Level Haircell	P-K Cashmere	P-3 Velour Matte	P-8 Suede	P-1 Haircell	36 Standard Colours	Stock Colours Available	Granite: n Integral 1 Capped	Wood Grain Patterns	Metallics	Over 4000 Custom Colours	Grade
n	33.90 N-m 300 in-lbf	n						n				n	n				n	KYDEX [®] HD Integral Colours
n	48.58 N-m 430 in-lbf			n	n	n	n	n	n	n	n	n					n	KYDEX [®] XD Integral Colours
n	35.06 N-m 310 in-lbf			n						n			n		n			KYDEX [®] WG Wood Grain Cap
n	50.84 N-m 450 in-lbf				n					n					n			KYDEX [®] 152 WG Wood Grain Cap
n	42.93 N-m 380 in-lbf		n		n	n	n	n	n	n	n			n				KYDEX [®] 130 Integral Granite
	62.14 N-m 550 in-lbf				n	n		n	n	n	n	n		1			n	KYDEX [®] 510 Granite Cap
n	37.28 N-m 330 in-lbf		n		n	n		n	n	n						n		KYDEX [®] 110 Integral Metallic

KYDEX[®] Sheet Colours

KYDEX® sheet is currently available in over 4,000 colours, granite, metallic and wood grain patterns, multiple surface textures and thicknesses from 0.56mm to 12mm. If none of these choices meet your needs, we'll make a custom colour just for you.





KYDEX® 3D Laminates Stock Colours



Thicknesses



Patterns

KYDEX [®] 130 Gra	nites	
Rosestone 82101	Black 82503	Glass Green 82303
KYDEX [®] 510 Gra Shown with black		y or clear cap also ava
Pastel Blue 42031	Black 42114	Pewter Gray 52001
11 2 1 2 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1		
Sandy Beach 72179	Beige Nebula 72646	
KYDEX [®] 110 Me	tallic Colours	
Copper 82103	Strawberry Pop 82108	Ductile Gold 82202
Olympic Cast 82406	Royal Garb 82407	Silver 82507
KYDEX [®] WG and Shown 50% of a	KYDEX [®] 152 WG ctual size	



Surface Textures



NOTE: Texture can influence the appearance of any colour. P-A and P-H textures are not available in all thick-



Chip chain sample kits containing KYDEX® sheet colours, metallics, granites, surface textures and sheet thicknesses are available through the Customer Service Department. 800.325.3133

Outside the US: +1.570.389.5814 Or visit www.kydex.com to order a sample kit or complete a Custom Colour Match form.

Navy Blue 82401

Desert Sand 82703

ailable



Steel Gray 52068



Pinstripe 52070

Lemon Star 82206

Pearl 82606 Bronze 82704

82305

Shimmering Forest

Candlelight

Tundra Birch

Honey Maple



P-H Seville

P-K Cashmere



History

KYDEX, LLC, is the manufacturer of KYDEX[®] sheet—a leading brand of durable thermoplastic sheet products with a reputation for excellence. Its sheet products are in demand around the globe.

Introduced by Rohm and Haas Company in 1965 for aircraft interior applications, the KYDEX[®] product line was purchased by U.S.-based KYDEX, LLC, in 1987. Since that time, the company has grown its brand by developing specialised grades to satisfy the needs of a wide range of customer and compliance requirements, emerging applications, and diverse industries.

Today, proprietary KYDEX[®] thermoplastic sheet is produced in Bloomsburg, PA, USA, at the company's ISO 9002: 2000 and ISO 14001 certified manufacturing facilities. KYDEX's customer-centric approach to manufacturing provides fast setup and cost-effective production of quality sheets and rolls—handling small runs, short lead times, and custom orders with ease and assurance.

Worldwide, a network of factory-trained sales professionals and customer service personnel are committed to supporting specifiers and customers with expert advice on designing and producing components that benefit from the outstanding properties of KYDEX[®] sheet.

Environmental Policy

For KYDEX, LLC, environmental responsibility has been an essential part of its business philosophy for more than 20 years. Every KYDEX® thermoplastic sheet product is produced and sold in keeping with the company's commitment to and regard for safety, health, and environmental protection. KYDEX's ISO 14001 certified manufacturing operations and R&D facilities ensure regulatory compliance while helping to protect resources, minimise waste, and reduce environmental impacts. In addition, KYDEX® thermoplastic sheet is 100% recyclable—making it an environmentally sound alternative to other products.



ISO 9001:2000 | ISO 14001:2004 Certified 6685 Low Street Bloomsburg, PA 17815 USA Phone: +1.570.387.6997 Fax: +1.570.387.8722 info@kydex.com

www.kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our products in the infringement of any patent.

This information supersedes all previously published data.